ASTM A500

Cold-Formed ERW Welded Carbon Steel Structural Tubing In Rounds and Shapes in Grades B and C

All of Nucor Tubular's structural tubing is produced in accordance with the mechanical and chemical property requirements of ASTM A500, Grades B & C.

Chemical Composition	Grade B	Grade C
Carbon, max %	0.26	0.23
Manganese, max %	1.35	1.35
Phosphorus, max %	0.04	0.04
Sulphur, max %	0.04	0.04
Copper, when copper steel is specified, min %	0.20	0.20

Mechanical Properties	Grade B	Grade C
Tensile Strength, min psi	58.000	62.000
Yield Strength, min psi	46,000	50,000
Elongation in 2" min	23%*	21%**
*0.180" wall and over		1
**0.120" wall and over		

Outside Dimension Tolerances for Square And Rectangle Structural Tubing

Largest Outside Dimension (in)	Plus/minus*
2 ½" and under	0.020
2 ½" to 3 ½"	0.025
3 ½" to 5 ½"	0.030
5 ½" and over	1%

*Tolerances include allowance for convexity or concavity. For rectangular tubing having a ratio of outside large to small flat dimension less than 1.5, and for square tubing, the tolerance on small flat dimension shall be identical to the large flat dimension tolerance. For rectangular tubing having a ratio of outside large to small flat dimension in the range of 1.5 to 3.0 inclusive, the tolerance on the small flat dimension shall be 1.5 times the large flat dimension tolerance. For rectangular tugging having a ratio of outside large to small flat dimension greater than 3.0, the tolerance on the small flat dimension shall be 2.0 times the large flat dimension tolerance.

NUCOR® TUBULAR PRODUCTS

Permissible Variation in Twist for Square and Rectangular Structural Tubing

Specified Outside Large	Maximum twist in 3 feet	
Flat dimension		
Over 1 ½" to 2 ½ "	0.062"	
Over 2 ½" to 4"	0.075″	
Over 4" to 6"	0.087″	
Over 6" to 8"	0.100″	
Over 8"	0.112″	

Notes:

Straightness: 0.025" times the number of ft of total length

Squareness of Sides: For square and rectangular structural tubing, adjacent sides shall be square (90°), with a permissible variation of 2° max.

Radius of corners: The radius of any outside corner shall not exceed 3.0 times the specified wall thickness.

Wall thickness: ±10% of nominal wall thickness, as measured at the center of the flat.

www.nucortubular.com